

D-8884 850

NATIONAL BUREAU OF STANDARDS WASHINGTON DC SURFACE S-ETC F/6 20/6
INFRARED SPECTRA OF METHYL ISOCYANIDE CHEMISORBED ON RHODIUM.(U)
MAY 80 R R CAVANAUGH, J T YATES

N00014-80-F-0008

UNCLASSIFIED


TR-16

NL

[of]
ALIA
[]



END
DATE
FILMED
6-80
DTIC



ADA 084850

LEVEL II

①
CH

OFFICE OF NAVAL RESEARCH
Contract N0014-80-F-0008

Technical Report #16

Infrared Spectra of Methyl Isocyanide Chemisorbed on Rhodium

R. R. Cavanagh and John T. Yates, Jr.

Surface Science Division
National Bureau of Standards
Washington, DC 20234

May, 1980

Reproduction in whole or in part is permitted for
any purpose of the United States Government

Approved for Public Release; Distribution Unlimited

To be published in the J. Chem. Physics

DTIC
ELECTE
MAY 29 1980
S C D

DDC FILE COPY

80 5 29 040

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER (9) Technical Report, 116	2. GOVT ACCESSION NO. AD-A084 850	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) (6) Infrared Spectra of Methyl Isocyanide Chemisorbed on Rhodium.		5. TYPE OF REPORT & PERIOD COVERED (D)
7. AUTHOR (10) R. R. Cavanagh and John T. Yates, Jr.		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Surface Science Division/ National Bureau of Standards Washington, DC 20234		8. CONTRACT OR GRANT NUMBER(s) N014-87-F-0008 Mod. No. 2-00007
11. CONTROLLING OFFICE NAME AND ADDRESS	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	12. REPORT DATE (11) May 1980
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	13. NUMBER OF PAGES
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited		13a. DECLASSIFICATION/DOWNGRADING SCHEDULE
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) (14) TR-16		
18. SUPPLEMENTARY NOTES Preprint; to be published in J. Amer. Chem. Soc.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Aluminum oxide; chemisorption; infrared spectroscopy; isomerization; methylisocyanide; rhodium		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The chemisorption of CH_3NC on dispersed Rh supported on Al_2O_3 has been investigated using transmission infrared spectroscopy. Evidence for the chemisorption of undissociated CH_3NC is presented. It is shown that at 300K the isomerization of CH_3NC to CH_3CN does not occur on Rh. The spectra obtained for adsorbed CH_3NC suggest an analogous chemistry of the Rh surface sites to that found in organometallic chemistry.		

DD FORM 1473
1 JAN 73EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

410655 Lm

INFRARED SPECTRA OF METHYL ISOCYANIDE CHEMISORBED ON RHODIUM

R. R. Cavanagh* and J. T. Yates, Jr.

Surface Science Division

National Bureau of Standards

Washington, D.C. 20234

*NRC-NBS Postdoctoral Research Associate 1978-1980

Comparison of the spectra obtained at 300°K on Al_2O_3 and on $\text{Rh}/\text{Al}_2\text{O}_3$ is shown in Figure 1b and 1c. Predominant features in the Rh sample are clearly absent in the Al_2O_3 spectrum. Carbon-hydrogen stretching modes are observed at 3003(s), 2946(s), 2918, 2883, 2861, and 2813 cm^{-1} . The features between 2300 and 2100 cm^{-1} are assigned to $\text{N}\equiv\text{C}$, as is the feature at 1910 cm^{-1} . For liquid CH_3NC the $\text{C}\equiv\text{N}$ stretching mode is at 2161 cm^{-1} .⁷ The bands at 1448(s), 1415(s), and 1391 cm^{-1} are assigned to CH_3 bending modes. Comparable CH_3 modes for liquid CH_3NC are at 3002 and 2951 cm^{-1} and 1456 and 1414 cm^{-1} .⁷

Subsequent exposure to 50 torr of CO is shown in Figure 1d. A single new feature at 2020 cm^{-1} is observed. The low intensity of this CO feature and the absence of the well-established intense spectrum of CO on $\text{Rh}/\text{Al}_2\text{O}_3$ indicates that methyl isocyanide has almost completely blocked specific Rh-CO binding sites.

Similar chemisorption experiments were conducted with methyl cyanide (CH_3CN). At 300K, no spectral features associated with CH_3CN adsorption on Rh were detected at 10 torr pressure. Following this experiment, the $\text{CH}_3\text{CN(g)}$ was pumped away and CO chemisorption was carried out. The CO spectrum which developed was identical to that found for freshly prepared rhodium surfaces.⁽⁵⁾ The absence of spectral features for CH_3CN and the capacity of the surface for CO adsorption following CH_3CN exposure suggests that CH_3CN is not chemisorbed by Rh at 300°K. These results, when combined

with the evidence for strong CH_3NC chemisorption and CO-blockage by the $\text{CH}_3\text{NC}(\text{ads})$ suggest the absence of surface-induced isomerization of CH_3NC to CH_3CN at 300°K , a process which is $\sim 63 \text{ kJoule mole}^{-1}$ exothermic in the gas phase, with an activation energy of $161 \text{ kJoule mole}^{-1}$.⁶

The possibility that the methyl isocyanide dissociates to CH_3 and CN fragments on the metal sites has also been addressed. Confirmation of the lack of dissociation of CH_3NC on Rh at 300K was obtained by comparison of the CH_3 (stretching and bending) features for Rh-CNCH₃ and physisorbed CH_3NC on Al_2O_3 at 190°K . In both regions the primary spectral features agree to within 10 cm^{-1} , although major changes are observed in relative band intensity within the C-H bending region.

These preliminary results indicate that at least in the Rh/ Al_2O_3 system, the analogy between the chemistry of CO and isocyanides can be extended to surfaces. Experiments are underway to further explore the behavior of isocyanides on supported metals and on single crystals.

REFERENCES

1. L. Malatesta and F. Bonati, Isocyanide Complexes of Metals (Wiley and Sons, New York, 1969).
2. J. C. Hemminger, E. L. Muetterties, and G. A. Somorjai, J. Am. Chem. Soc. 101 62 (1979).
3. W. L. Jorgensen and L. Salem, The Organic Chemist's Book of Orbitals. (Academic Press, New York, 1973).
4. J. Casanova, Jr., R. E. Schuster, and H. D. Werner, J. Chem. Soc. 4280 (1963).
5. J. T. Yates, Jr., T. M. Duncan, S. D. Worley, and R. W. Vaughan, J. Chem. Phys. 70 1219 (1979).
6. F. W. Schneider and B. S. Rabinovitch, J. Amer. Chem. Soc. 84, 4215 (1962).
7. G. Herzberg, Molecular Spectra and Molecular Structure II. IR and Raman Spectra of Polyatomic Molecules, Van Nostrand, New York, 1945, p. 332.

Figure 1. Infrared spectra at 300K for CH_3NC on $\text{Rh}/\text{Al}_2\text{O}_3$. Spectrum (a): Background spectrum of Al_2O_3 (11.4 mg/cm^2) following H_2 reduction; spectrum (b): Saturation coverage of CH_3NC on Al_2O_3 followed by evacuation; spectrum (c): CH_3NC saturation of 2.8% $\text{Rh}/\text{Al}_2\text{O}_3$ (16.3 mg/cm^2) followed by evacuation; spectrum (d): Addition of ~ 50 torr CO to (c).

